

Metl-Clad QD Primer

Quick Dry Rust Inhibitive Primer

Product Data Sheet

DESCRIPTION and USES

This quick drying, versatile primer has many uses. It contains Barium Metaborate, a non-toxic rust inhibiting pigment that controls corrosion on iron and steel surfaces. It is an excellent adhesion promoting primer on galvanized metal, plastic, aluminum and wood. This primer may be used under all conventional top coats as well as epoxies and lacquers.

SURFACE PREPARATION

All surfaces to be primed must be dry and free of dirt and grease. Wash all oily surfaces with a commercial degreaser. Remove rust and scale by sand blasting or power brushing.

APPLICATION

Spray application is preferred. Brush or roller may be used on small areas. Do not apply at temperatures below 40°F or at temperatures above 85°F. Use as supplied. Thinning this product will bring it out of compliance with current VOC regulations. DON NOT THIN.

SAFETY INFORMATION

NOTICE: Reports have associated repeated and prolonged occupational exposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. For complete safety information, refer to the SAFETY DATA SHEET for this product.

COLORS

White (May be tinted with up to 4 oz. of 866 Colorant per gallon).

The suggestions for use and technical data here given are accurate to the best of our knowledge and are offered in good faith. Because the conditions and use of our products are beyond our control, our liability, if any, is limited to the replacement of defective material only. RepcoLite Paints, Inc. DISCLAIMS ALL OTHER WARRANTIES relating to our products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION, expressed or implied, INCLUDING but not limited to warranties of merchantability and fitness for a particular purpose. TECHNICAL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE.

TECHNICAL DATA

Vehicle Type: Linseed/Tung Oil Phenolic Resin

Volume Solids: 47%

Coverage: 300 – 400 SF/Gallon

Dry Time:

Touch: 20 – 30 Minutes

Recoat: 1 Hour on non-porous surfaces

8 Hours on porous surfaces

VOC: Less than 450 g/l

Clean Up: Xylene

PRODUCT CODE INFORMATION

44810 Metl-Clad QD Primer—White

RepcoLite Paints, Inc.

473 W. 17th St. Holland, MI 49423 (616) 396-1275 www.repcolite.com