

DESCRIPTION and USES

Port City Log Cabin Wood Finish is a penetrating exterior wood finish designed to protect and enhance the natural grain and texture of the wood. Its unique formula allows the wood to "breathe" and provides protection against harmful UV rays. It is ideal for vertical surfaces like siding and fences and can also be used on outdoor furniture. However, it is not recommended for horizontal surfaces, such as decks, and should not be applied over surfaces that have already been stained or coated with other clear wood finishes or preservatives without proper preparation.

PREPARATION

Surface Preparation: All cutting, gluing, and sanding of the wood should be done before coating. Surfaces to be stained must be clean, dry, and free of contaminants such as dirt, oil or wax. If mildew is present, clean the surface with 1 part household bleach to 10 parts water solution. New pressure-treated wood should be allowed to dry for at least 30 days. New cedar should have the mill glaze removed through sanding or an oxalic acid-based cleaning/brightener product. Discoloration can be removed and the wood restored to its natural color by using a wood brightener. Rinse well after these treatments. Wear protective gloves, clothing, and goggles when working with bleach or wood brightener. Power washing to remove old or peeling stain is recommended. Allow 2 days for wood to dry after rain, rinsing, or power washing before staining.

APPLICATION

Stir thoroughly before and occasionally during use. Apply with natural bristle brush making sure all areas, especially edges, are well coated, brushing in the direction of the wood grain. On bare wood surfaces apply three coats, allow 24 hours to dry between coats. Avoid application, if possible, when temperatures are above 90°F or below 50°F, when relative humidity is above 85%, or direct sunlight. Use as supplied. Do not thin. Every 2-3 years a complete re-coating may be necessary, a yearly inspection can determine when re-coating is needed. **Port City Log Cabin Maintenance Coat** may also be used to preserve existing color from previous applications of **Port City Log Cabin Wood Finish**.

CLEAN UP

Clean painting tools immediately after use with specified clean up solvent. Use same clean up solvent to clean dried product off equipment.

COLORS

Available in Cedar, Cypress, Butternut, and Mahogany.

REGULATORY INFORMATION

For complete safety information, refer to the SAFETY DATA SHEET for this product.

The suggestions for use and technical data here given are accurate to the best of our knowledge and are offered in good faith. Because the conditions and use of our products are beyond our control, our liability, if any, is limited to the replacement of defective material only. RepcoLite Paints, Inc. DISCLAIMS ALL OTHER WARRANTIES relating to our products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION, expressed or implied, INCLUDING but not limited to warranties of merchantability and fitness for a particular purpose. TECHNICAL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE.

TECHNICAL DATA

Finish:	Low Lustre
Vehicle Type:	Alkyd Resin
Weight Solids:	52-53%
Volume Solids:	44-45%
Density:	7.8-7.9 lb/gal
Coverage:	250-300 SF/Gallon
Dry Time:	
<i>Touch:</i>	8 hours
<i>Recoat:</i>	24 hours
Clean Up:	Paint Thinner (Mineral Spirits)
VOC:	< 450 g/L
Compliance:	As of 03/05/2026
	Federal: Yes
	OTC Phase 1: No
	OTC Phase 2: No

PRODUCT CODE INFORMATION

45860	Port City Log Cabin – Cedar
45861	Port City Log Cabin – Cypress
45862	Port City Log Cabin – Butternut
45863	Port City Log Cabin – Mahogany
45869	Port City Log Cabin Maintenance Coat Clear