

DESCRIPTION AND USES

Mira-Poxy 100% Solids High Build Epoxy is a premium epoxy coating designed for application to interior surfaces where an extremely high build coating is desired, such as bar tops. It can be applied in a single coat at thicknesses of 1/2 inch or more. The resulting very clear, high gloss finish is extremely durable and resistant to stains and chemical attack. If a lower gloss surface is desired, Mira-Poxy may be topcoated with a wide variety of finish products depending on intended use. Mira-Poxy has no odor, contains no VOCs, and will adhere well to virtually any surface. It is not suitable for exterior use.

SPECIFICATIONS

SURFACE PREPARATION and APPLICATION: Mira-Poxy is a unique product that requires specific application techniques. Please refer to the product application bulletin for complete, detailed surface preparation, mixing, and application instructions.

CLEAN UP: Use Acetone or Xylene.

PRECAUTIONS

Avoid contact with skin and eyes. Allow unused material to harden in the mixing container before disposal. Detailed health and safety information is available on the product Material Safety Data Sheet.

PRODUCT CODES

519C - Clear Gloss Component A
510X - Component B

TECHNICAL DATA

VEHICLE TYPE: Epoxy Amine

VOLUME SOLIDS: 100% (mixed)

WEIGHT SOLIDS: 100% (mixed)

DENSITY: 8.85 lbs/gal (mixed)

ACTUAL VOC: 0 lbs/gal

REGULATORY VOC: 0 g/L

SEALER: Self-seal (see product application bulletin)

CLEAN UP SOLVENT: Use Acetone or Xylene to clean tools immediately after application.

THEORETICAL COVERAGE: 1604 SF @ 1 mil

RECOMMENDED SPREAD RATE: 20 - 30 square feet @ 60-80 mils dry film thickness. 13 square feet @ 1/8" thick.

POT LIFE: 45 minutes

DRY TIME: Dry to touch in 8 hours. Recoat in 24 hours.

SHELF LIFE: Minimum 1 year shelf life when properly stored.

For complete safety information, refer to the SAFETY DATA SHEET for this product.

RepcoLite
Quality Paint Since 1946

RepcoLite Paints, Inc.
473 W. 17th St.
Holland, MI 49423
(616) 396-1275
www.repcolite.com