

DESCRIPTION AND USES

Mira-Var White Conversion Varnish Primer is a catalyzed varnish primer recommended for use as a first coat under **Mira-Var** topcoats. It features excellent filling, sealing and sanding properties. When used under **Mira-Var** topcoats, this system will provide high build and exceptional resistance properties. This system passes the KCMA performance standard and is recommended for use on kitchen cabinets and office furniture as well as any application where a high build, heavy duty wood coating is required.

SPECIFICATIONS

SURFACE PREPARATION: All wood surfaces to be finished must be clean, dry and free of contaminants such as oil or wax. Maple and birch should be sanded with 180 grit sandpaper prior to finishing. Moisture content of wood should be 7-9%. Oil-based stains should be allowed to dry a minimum of 24 hours before application of topcoat. Previously finished surfaces should be cleaned and thoroughly sanded with 220 grit sandpaper to ensure adhesion.

MATERIAL PREPARATION: **Mira-Var White Conversion Varnish Primer** is a 2 component system. Add 4 Fl. oz. **710X Catalyst** per gallon of **Mira-Var White Conversion Varnish Primer**.

APPLICATION: **Mira-Var White Varnish Primer** is designed for all types of spray application. Product comes ready to spray, but if thinning is necessary use Xylene. Because of the acid catalyst, all parts of equipment in contact with wet catalyzed coating must be stainless steel or plastic. Please refer to the supplier of your equipment for specifications on your particular requirements. Total film build should not exceed 4 dry mils. Stir all products well before use.

CLEAN UP: Use Lacquer Thinner to clean dried product off equipment.

PRECAUTIONS

This product is intended for use by properly trained professionals in a controlled environment. Always pre-test the product or system on the substrate you will be using and under your line conditions to confirm application suitability and to avoid the need for costly refinishing.

COMPANION PRODUCTS

- 720 Series Products
- 710X Catalyst
- 800 Series Stains, Glazes, and Toners
- 400 Series Stains and Fillers
- 910 Lacquer Thinner
- 950 Lacquer Retarder

PRODUCT CODES

720PW - White Primer

TECHNICAL DATA

VEHICLE TYPE: Coconut Alkyd

VOLUME SOLIDS: 37%

WEIGHT SOLIDS: 56%

DENSITY: 9.85 lbs/gal

VOC: 4.11 lbs/gal

REGULATORY VOC: 492 g/L

CATALYZATION: Use 4 Fl. Oz/gallon of **710X Catalyst**

POT LIFE: 10 hours

CLEAN UP SOLVENT: Lacquer Thinner

REDUCING SOLVENT: Xylene

COVERAGE: 596 square feet at 1 mil dry film thickness.

DRY TIME: Dry to the touch in 15-20 minutes, sand/re-coat in 45-60 minutes.

SHELF LIFE: 1 year shelf life when properly stored.

For complete safety information, refer to the SAFETY DATA SHEET for this product.

RepcoLite
Quality Paint Since 1946

RepcoLite Paints, Inc.
473 W. 17th St.
Holland, MI 49423
(616) 396-1275
www.repcolite.com

The suggestions for use and technical data here given are accurate to the best of our knowledge and are offered in good faith. Because the conditions and use of our products are beyond our control, our liability, if any, is limited to the replacement of defective material only. RepcoLite Paints, Inc. DISCLAIMS ALL OTHER WARRANTIES relating to our products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION, expressed or implied, INCLUDING but not limited to warranties of merchantability and fitness for a particular purpose. TECHNICAL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE.

Date: November 2015