

DESCRIPTION AND USES

Mira-Var PRO Conversion Varnish Sealer is formulated for high build and superior performance on a variety of wood substrates used in interior finishing. It is a fast-drying, easy-sanding sealer with superior film-building properties as well as mar, chemical and moisture resistant characteristics.

SPECIFICATIONS

SURFACE PREPARATION: All wood surfaces to be finished must be clean, dry and free of contaminants such as oil or wax. Maple and birch should be sanded with 180 grit sandpaper prior to finishing. Moisture content of wood should be 7-9%. Oil-based stains should be allowed to dry a minimum of 24 hours before application of topcoat. Previously finished surfaces should be cleaned and thoroughly sanded with 220 grit sandpaper to ensure adhesion.

MATERIAL PREPARATION: Mira-Var High Build Conversion Varnish is a 2 component system. Add 4 Fl. oz. 710X Catalyst per gallon of Mira-Var Conversion Varnish.

APPLICATION: Mira-Var Conversion Varnish is designed for all types of spray application. Product is ready to spray, but if reduction is necessary use Xylene. Because of the acid catalyst, all parts of equipment in contact with wet catalyzed coating must be stainless steel or plastic. Please refer to the supplier of your equipment for specifications on your particular requirements. Total film build should not exceed 4 dry mils. Stir all products well before use.

CLEAN UP: Use Lacquer Thinner to clean dried product off equipment.

PRECAUTIONS

This product is intended for use by properly trained professionals in a controlled environment. Always pre-test the product or system on the substrate you will be using and under your line conditions to confirm application suitability and to avoid the need for costly refinishing.

COMPANION PRODUCTS

- 730 Series Products
- 720 Series Sealers and Primers
- 710X Catalyst

PRODUCT CODES

730S - Clear Sealer

TECHNICAL DATA

VEHICLE TYPE: Coconut Alkyd

VOLUME SOLIDS: 30%

WEIGHT SOLIDS: 39%

DENSITY: 7.78 lbs/gal

VOC: 4.74 lbs/gal

REGULATORY VOC: 568 g/L

CATALYZATION: Use 4 Fl. Oz/gallon of 710X Catalyst

POT LIFE: 10 hours

CLEAN UP SOLVENT: Lacquer Thinner

REDUCING SOLVENT: Xylene

COVERAGE: 482 square feet at 1 mil dry film thickness.

DRY TIME: Dry to the touch in 15-20 minutes, sand/re-coat in 30-60 minutes.

SHELF LIFE: 1 year shelf life when properly stored.

For complete safety information, refer to the SAFETY DATA SHEET for this product.

RepcoLite
Quality Paint Since 1946

RepcoLite Paints, Inc.
473 W. 17th St.
Holland, MI 49423
(616) 396-1275
www.repcolite.com